

This page is mainly introduced the X5CrNi18-9 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of X5CrNi18-9, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels X5CrNi18-9

X5CrNi18-9 Standard Number:		
ITEM	Standard Number	Descriptions
1	ISO 16143-1 (2004)	Stainless steels for general purposes -- Part 1: Flat products
2	ISO 16143-2 (2004)	Stainless steels for general purposes -- Part 2: Semi-finished products, bars, rods and sections
3	ISO 16143-3 (2005)	Stainless steels for general purposes -- Part 3: Wire
4	ISO 6931-2	Stainless steels for springs - Part 2: Narrow strip
5	ISO 9327-5	Steel forgings and rolled or forged bars for pressure purposes - Technical delivery conditions - Part 5: Stainless steels
6	ISO 9328-5	Steel plates and strips for pressure purposes - Technical delivery conditions - Part 5: Weldable fine grain steels, thermomechanically rolled
7	ISO 9329-4	Seamless steel tubes for pressure purposes - Technical delivery conditions - Part 4: Austenitic stainless steels
8	ISO 9330-6	Welded steel tubes for pressure purposes - Technical delivery conditions - Part 6: Longitudinally welded austenitic stainless steel tubes
9	ISO/TS 15510 (2003)	Stainless steels - Chemical composition

X5CrNi18-9 Chemical composition(mass fraction)(wt.%)		
Chemical	Min.(%)	Max.(%)
C		0.07
Si		1.00
Mn		2.00
P		0.045
S		0.030
Cr	17.00	19.00
Mo	8.00	11.00
Ni		

X5CrNi18-9 Physical Properties		
Tensile strength	115-234	σ_b /MPa

Yield Strength	23	$\sigma_{0.2} \geq / \text{MPa}$
Elongation	65	$\delta 5 \geq (\%)$
ψ	-	$\psi \geq (\%)$
Akv	-	$Akv \geq / \text{J}$
HBS	123-321	-
HRC	30	-

X5CrNi18-9 Mechanical Properties

Tensile strength	231-231	σ_b / MPa
Yield Strength	154	$\sigma_{0.2} \geq / \text{MPa}$
Elongation	56	$\delta 5 \geq (\%)$
ψ	-	$\psi \geq (\%)$
Akv	-	$Akv \geq / \text{J}$
HBS	235-268	-
HRC	30	-

X5CrNi18-9 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

X5CrNi18-9 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	$\Phi 8$ -1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil / Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Stainless Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.

(3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter : 1mm-2000mm

Square bar:

Size: 50mm * 50mm-600mm *600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any imperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionalism.